County Highways Laboratory

Stockbridge Road, Micheldever Station, Hampshire, SO21 3BB Telephone:01962 774502

email: CountyHighwaysLab@hants.gov.uk



A0372-1

Lab No.:

Client: L & S Waste Mangement Ltd Pegham Industrial Estate

Laveys Lane

Fareham Hampshire

Steve Kew

PO15 6SD

F.A.O:

Particle Size Distribution Report

Aggregate testing: L & S May 2022 Project:

Portsdown Stock Location: Crushed Demolition Material:

Specification: SHW Clause 805 Type 3 Subbase

Contractor: N/A

L & S - Portsdown Supplier/Plant:

Date Sampled: 04/05/2022 Date Received: 04/05/2022

Sampled by: JH Tested by: FF

Sample Type: Bulk Date Tested: 26/05/2022


Test Mass (g): 16167 Site Ref.: JH1

> Test method: BS EN 933-1: 2012 Sampling Method: BS EN 932-1:1997 Preparation Method: BS EN 932-2: 1999

Sieve Size (mm) Percent passing Specification 80 100 100.0 40 90 80.0 - 99.0 20 73 50.0 - 78.0 10 47 31.0 - 60.0 4 23 18.0 - 46.0 2 18 10.0 - 35.0 1 15 6.0 - 26.0

13

4.3



Moisture content (%)	7.0
Uniformity Coefficient	51



0.5

0.063

Remarks The sample complies with the specification

<= 20.0

<= 5.0

Signed	The
Date	26/05/2022
Approved	E. Frost

Note: County Highways Laboratory only accepts responsibility for the accuracy of the results contained in this report. No responsibility can be accepted for the results being representative of the material or items sampled unless sampling has been carried out by County Highways Laboratory staff. This result may not be reproduced either in part or in full without the written permission of the County Highways Laboratory. The results stated in this report are only related to the items tested. For samples taken by the Client the results stated in this report are only related to the sample/s as received.